

TECHNICAL DATA SHEET

71602S

71602S is a LLDPE blown film grade produced by the Spherilene Technology

This grade can be used in General Purpose Packaging Film Application

The precise morphological control achieved during polymerization confers excellent processability & mechanical strengths

71602S is additivated with slip & antiblocking agent for good openability & slip properties

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238	g/10 min	2.0
Density (23°C)	ASTM D1505	g/cm ³	0.920
Film Property **			
Tensile Strength at Yield MD		MPa	12
Tensile Strength at Yield TD		MPa	11
Tensile Strength at Break MD	ASTM D882	MPa	28
Tensile Strength at Break TD	(500 mm/min)	MPa	20
Elongation at Break MD		%	500
Elongation at Break TD		%	750
Elmendorf Tear Strength MD	ASTM D1992	g	60
Elmendorf Tear Strength TD		g	300
Dart Impact Strength, F ₅₀ (38 mm Dart, 66 cm Height)	ASTM D1709A	g/μm	3
Suggested Processing Conditions			
Barrel Temperature		°C	170 - 200
Melt Temperature		°C	190 - 200
Blow up Ratio		-	2.0 - 3.0
Die Gap		mm	2.0 - 2.5

* Halene L is the registered trademark of Linear Low Density Polyethylene of HPL

** Typical values with 25 μm film made with 2.5 mm die gap & BUR 2.5

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.
Visit us at www.haldia Petrochemicals.com