

## TECHNICAL DATA SHEET

## M6007LU

**M6007LU** is a Narrow MWD HDPE produced by Spherilene Technology

**M6007LU** is ideally suited for injection molding of heavy duty Crates & Industrial products

**M6007LU** is stabilized adequately with HALS\* to give long service life under outdoor exposure

The precise control of morphology & MWD during polymerization confers superior processability & improved performance properties compared to conventional HDPE grades

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238	g/10 min	7.5
Density (23°C)	ASTM D1505	g/cm <sup>3</sup>	0.950
<b>Physical Property</b>			
Tensile Strength at Yield	ASTM D638	MPa	24
Elongation at Break	(50 mm/min)	%	>500
Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	50
Flexural Modulus	ASTM D790A	MPa	850
Hardness	ASTM D2240	Shore D	62
Spiral Flow Length @ 235°C	HPL Method	mm	430
DSC Melting Temperature	ASTM D3418	°C	132
<b>Suggested Processing Conditions</b>			
Barrel Temperature		°C	185 - 235
Nozzle Temperature		°C	200 - 235

\* Halene H is the registered trademark of High Density Polyethylene of HPL

Mechanical Properties are on Injection Molded test specimens prepared as per ASTM D4101

+ The total Hindered Amine Light Stabiliser (HALS) content is ~ 2000 ppm

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.  
Visit us at [www.haldiapetrochemicals.com](http://www.haldiapetrochemicals.com)