

TECHNICAL DATA SHEET

P5200UV

P5200UV is a pipe grade HDPE, produced by the Mitsui CX Technology

P5200UV is stabilized adequately with HALS⁺ to give a long service life under outdoor exposure & recommended for telecom ducts

P5200UV combines excellent processability with good creep resistance, ESCR and mechanical properties

Property	Test Method	Unit	Value
Melt Flow Index (5 kg, 190 °C)	ASTM D1238	g/10 min	0.8
Density (27 °C)	ASTM D1505	g/cm ³	0.948
Physical Property			
Tensile Strength at Yield		MPa	25
Elongation at Yield	ASTM D638	%	7
Tensile Strength at Break	(50 mm/min)	MPa	38
Elongation at Break		%	650
Notched Izod Impact Strength (23 °C)	ASTM D256A	J/m	175
Flexural Modulus	ASTM D790A	MPa	1000
Hardness	ASTM D2240	Shore D	65
ESCR (F ₅₀ , 10% Igepal soln. v/v)	ASTM D1693B	Hr	> 1000
Vicat Softening Point (10 N)	ASTM D1525	°C	121
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	67
Oxidative Induction Time	ASTM D3895	Min	> 30
Suggested Processing Conditions			
Barrel Temperature		°C	150 - 180
Die Temperature		°C	170 - 180

* Halene H is the registered trademark of High Density Polyethylene of HPL

Mechanical Properties are on specimens from Compression Molded sheets

⁺ The total Hindered Amine Light Stabiliser (HALS) content is ~ 2000 ppm

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.
Visit us at www.haldia Petrochemicals.com