

## TECHNICAL DATA SHEET

## M5025L

**M5025L** is an Injection Molding HDPE produced by Spherilene Technology

This resin is particularly recommended for general purpose Injection Molded items & Masterbatch application

**M5025L** combines excellent processability with good mechanical properties

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238	g/10 min	30.0
Density (23°C)	ASTM D1505	g/cm <sup>3</sup>	0.950
<b>Physical Property</b>			
Tensile Strength at Yield	ASTM D638	MPa	20
Elongation at Break	(50 mm/min)	%	250
Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	28
Flexural Modulus	ASTM D790A	MPa	800
Hardness	ASTM D2240	Shore D	62
Spiral Flow Length @ 235°C	HPL Method	mm	730
Vicat Softening Point (10 N)	ASTM D1525	°C	125
Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	77
DSC Melting Temperature	ASTM D3418	°C	132

### Suggested Processing Conditions

Barrel Temperature	°C	180 - 235
Nozzle Temperature	°C	235

\* Halene H is the registered trademark of High Density Polyethylene of HPL

Mechanical Properties are on Injection Molded test specimens prepared as per ASTM D4101

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.  
Visit us at [www.haldiapetrochemicals.com](http://www.haldiapetrochemicals.com)